



HS-715
MONO FILAMENT TAPE

PHYSICAL PROPERTIES 物理特性	STANDARD 英制	METRIC 公制	TEST METHOD 测试方法	
REINFORCEMENT 加强	GLASS FIBER			
ADHESIVE 胶水	synthetic rubber			
BACKING 基材	PET			
COLOR 颜色	CLEAR			
TOTAL THICKNESS 总厚度	4.7MIL	0.12MM	ASTM D-3652	GB/T7125
PEEL ADHESION 剥离强度	72OZ/IN	20N/25MM	ASTM D-3330	GB/T2792
HOLDING POWER 保持力	》 24H	》 24H	ASTM D-3654	GB/T4851
TENSILE STRENGTH 抗拉强度	126LBF/IN	550N/25MM	ASTM D-3759	GB/T7753
ELONGATION AT BREAK 断裂伸长率	4%	4%	ASTM D-3759	GB/T7753
SERVICE TEM -MINI 低温	-5℃		BC/BD -220SE	
SERVICE TEM -MAX 高温	70℃		DHG-9055A	

DESCRIPTION OF PRODUCT

产品描述

单向纤维胶带，耐曲折性好，特制胶粘剂，适用于中等强度的所有包装固定，以及锂电池的捆扎。

HS-715 Backed with PET film and reinforced with glass fiber. Specially formulated adhesive. It's high strength mono-directional filament tape with good resistance to abrasion

APPLICATION 应用

all types of packaging with medium strength and bundling lithium batteries.
中等强度的所有包装固定以及锂电池的捆扎

保质期： 妥善保持，发货1年
shelf life : keeping well, 1 year after shipment

Storage Condition:
It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4℃ to 26℃ and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of our product. we do not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. we strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. we assume no responsibility for any damage or injury sustained as a result of the use of its products.

NANTONG HUISEN ADHESIVE TECHNOLOGY CO.,LTD

ADD:NO 16 WEST YUELONG RODA ,RUGAO ECONOMIC DEVELOPMENT ZONE JIANGSU CHINA 226500
POST CODE:226500 TEL:86-0513-87301808

