



HS-930
high strength double Sided Cross Filament Tape

PHYSICAL PROPERTIES 物理特性	STANDARD 英制	METRIC 公制	TEST METHOD 测试方法	
REINFORCEMENT 加强	GLASS FIBER			
ADHESIVE 胶水	synthetic rubber			
BACKING 基材	Glassine Paper			
COLOR 颜色	YELLOW			
TOTAL THICKNESS 总厚度	10.6MIL	0.27MM	ASTM D-3652	GB/T7125
PEEL ADHESION 剥离强度	128OZ/IN	35N/25MM	ASTM D-3330	GB/T2792
HOLDING POWER 保持力	》 24H	》 24H	ASTM D-3654	GB/T4851
TENSILE STRENGTH 抗拉强度	80LBF/IN	350N/25MM	ASTM D-3759	GB/T7753
ELONGATION AT BREAK 断裂伸长率	5%	5%	ASTM D-3759	GB/T7753
SERVICE TEM-MINI 低温	-5℃		BC/BD -220SE	
SERVICE TEM -MAX 高温	70℃		DHG-9055A	

DESCRIPTION OF PRODUCT

产品描述

高强度双向纤维双面胶带，高粘性，对各种被粘贴物具有较高的粘接力，适用于贴合地毯、橡胶制品、无纺布、皮革等。

HS-930 Backed with glassine paper and reinforced with crossed glass fiber. Specially formulated adhesive.

High-strength bidirectional fiber double-sided adhesive tape with high adhesion to various substrates, suitable for bonding carpets, rubber products, non-woven fabrics, leather, etc.

APPLICATION 应用

suitable for bonding carpets, rubber products, non-woven fabrics, leather, etc.

保质期： 妥善保持， 发货1年

shelf life : keeping well, 1 month after shipment

Storage Condition:

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4℃ to 26℃ and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of our product. we do not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. we strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. we assume no responsibility for any damage or injury sustained as a result of the use of its products.

NANTONG HUISEN ADHESIVE TECHNOLOGY CO.,LTD

ADD:NO 16 WEST YUELONG RODA ,RUGAO ECONOMIC DEVELOPMENT ZONE JIANGSU CHINA 226500
POST CODE:226500 TEL:86-0513-87301808

